

Technical Data

envisionTEC WIC 100G Series

The **envisionTEC** WIC100G resin has been formulated for the casting of model made on the Perfactory® market. Its nano wax content offers a clean burn out with the highest reproduction details. The material can be processed on all Perfactory® products from **envisionTEC**.

Description

Wax casting is easy from the **envisionTEC** WIC100G resin when using a standard wax burn out cycle with a regular gypsum investment. During the burn out cycle, the nano wax melts away first allowing the resin to burn off without excessive expansion or pressure from degassing which is a problem normally associated with polymer based materials during the burn out cycle.

envisionTEC WIC100G is a photo cured hybrid resin system that produces the highest quality part details without sacrificing strength, ease of handling, and finishing.

Application

Highest quality detailed parts, excellent burn out properties, and high speed building allows the **envisionTEC** WIC100G to be optimal for use in Jewelry market for production of master patterns for direct investment casting.

Mechanical Properties*

Method	Description	Value
DIN 1342-2 DIN EN ISO 527-1 DIN EN ISO 527-1	Viscosity Tensile Strength Elongation at Break	4.200 cps 14.8 MPa 6.3 %
DIN ISO 1183-1	Density	1.32g/cm ³
DIN EN ISO 868	Hardness (Shore D)	80 Shore
DIN 53765	Ignition Temperature	300 °C

Cleaning, drying and post curing is to be carried out as described in **envisionTEC**'s postprocessing instructions for this material. Recommendation: use incubator. Post curing of parts in Otofash G171.

*All data provided is preliminary data and must be verified by the individual user.

